



COTTON AND POLYESTER

					Standard	Low Temperature	Quick application on to Cotton, Polyester, Poly-Cotton	
POLYURETHANE	70-80µm	Flex blade 45°	Medium to high Pressure		120°C	110-115°C	140°C	HOT or COLD Peel
					20s	25-30s	5/7s	

NYLON

					Standard			
POLYURETHANE	70-80µm	Flex blade 45°	Medium to high Pressure			140°C		HOT Peel
						20-25s		

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flex regular blade.
2. Weed the excess material.
3. Heat press on the garment following instructions (time and temperature) & Protect the polyester carrier with silicone paper.
4. Peel the carrier off when cold or hot.



THICKNESS: 70-80 microns

CARRIER: Adhesive & Transparent polyester

CERTIFICATES: Oeko-Tex Label Standard 100 Class I



APPLIES ON

Cotton ● Polyester ● Acrylic ● Similar Fibres ● Nylon

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60°C : Cotton & Polyester
Max 40°C : Nylon
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

Vizuell AS

Sundvolden Næringspark, Åsaveien 89b, 3531 Krokkleiva
32 16 16 20 - post@vizuell.no - vizuell.no

NOTE: For best results, it is recommended to TEST prior to starting standard production